isosplit



Tubo rame ACR preisolato anticondensa specifico per impianti Split-System.
Pre-insulated, ACR copper pipe, with condensation barrier designed specifically for split systems.

Caratteristiche Tubo rame
Rame ACR ricotto (R220), caratteristiche meccaniche, dimensioni, tolleranze ed eccentricità rispondenti alla normativa UNI EN 12735-1 o secondo specifiche tecniche del cliente. Utilizzabile con fluidi refrigeranti R407C e R410A, pulizia interna e deumidificazione con gas inerte con residuo complessivo max 0,034 gr/mq ed estremità sigillate come da ASTM B280.

Properties of Copper pipe
ACR annealed (R220) copper; mechanical properties, dimensions, tolerances and eccentricity in conformity with standard UNI EN 12735-1. Can be used with refrigerants R407C and R410A gases, internal cleaning and dehumidifying with inert gas with max overall residue 0.034 g/sq m and ends sealed as laid down by ASTM B280.

Rivestimento
Guaina isolante in polietilene espanso reticolato fisico a cellule chiuse con i seguenti valori tecnici:

- conducibilità termica a 40°C $\lambda \leq 0{,}040$ W/m*K
- fattore di resistenza alla diffusione del vapore acqueo (anticondensa) $\mu \geq 15000$
- reazione al fuoco classe 1
- temperatura di utilizzo -80°/+120°C
- non contiene CFC

Insulation
Closed-cell physically cross-linked expanded polyethylene insulating sheath with the following specifications:

- thermal conductivity at 40°C $\lambda \leq 0.040$ W/m*K
- water vapour diffusion resistance (anti-condensation) factor $\mu \geq 15000$
- reaction to fire class 1
- operating temperature -80°/+120°C
- CFC free

Pellicola esterna in Polietilene estruso (LDPE) colore bianco, adittivata con ritardante in fiamma, aderente all'espanso in modo da garantire un grado di anticondensa elevato, ottima resistenza alle abrasioni e alle lacerazioni.

External protective film (LDPE) in extruded polyethylene, white colour, with added flme retardant, adherent to expanded foam in order to guarantee a high level of anti-condensation, high resistance to abrasion and tears.

Ø Tubo rame mm (inch)	Spessore Tubo rame mm	Peso nominale Tubo rame gr/m	Spessore isolante mm	Pressione max Esercizio Bar	Lunghezza Rotoli mt
Ø Copper pipe mm (inch)	Thickness Copper pipe mm	Nominal weight copper pipe gr/m	Insulation Thickness mm	Max working pressure Bar	Roll Length mt
6,35 (1/4″)	0,80	126	6	130	25-50
9,52 (3/8″)	0,80	198	7	87	25-50
12,7 (1/2″)	0,80	270	7	70	25-50
6,35 (1/4″)	1	150	6	150	25-50
9,52 (3/8″)	1	238	7	100	25-50
12,7 (1/2″)	1	327	7	80	25-50
15,87 (5/8″)	1	416	9	63	25-50
19,05 (3/4″)	1	505	9	58	25
22,22 (7/8″)	1	600	9	50	25

Zecchini srl
Viale dell'industria, 60
Cittadella (PD) 35013
Tel 049 5970300
Fax 049 9404633
info@zecchinisrl.it
www.zecchinisrl.it

ZECCHINI
tubi rivestiti e preisolati